

Mo-6283/WW-5514

U.S. APPLICATION NO. (If known, see 37 CFR 1.5)

To be assigned 09/807094

TRANSMITTAL LETTER TO THE UNITED STATES
DESIGNATED/ELECTED OFFICE (DO/EO/US)
CONCERNING A FILING UNDER 35 U.S.C. 371

INTERNATIONAL APPLICATION NO.

PCT/EP99/07349

INTERNATIONAL FILING DATE

04 October 1999 (4.10.99)

PRIORITY DATE CLAIMED

16 October 1998 (16.10.98)

TITLE OF INVENTION HIGH LUSTER, FLEXIBLE MULTILAYERED FILM WITH A POLYAMIDE OUTER LAYER CONTAINING
NANODISPERSED FILLING MATERIAL AND UTILIZATION OF SAID FILM FOR PACKAGING FOODSTUFFS

APPLICANT(S) FOR DO/EO/US Holger Eggers; Gregor Kaschel

Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:

1. ☒ This is a **FIRST** submission of items concerning a filing under 35 U.S.C. 371.
2. ☐ This is a **SECOND** or **SUBSEQUENT** submission of items concerning a filing under 35 U.S.C. 371.
3. ☒ This is an express request to begin national examination procedures (35 U.S.C. 371(f)). The submission must include items (5), (6), (9) and (21) indicated below.
4. ☒ The US has been elected by the expiration of 19 months from the priority date (Article 31).
5. ☒ A copy of the International Application as filed (35 U.S.C. 371(c)(2))
 - a. ☒ is attached hereto (required only if not communicated by the International Bureau).
 - b. ☐ has been communicated by the International Bureau.
 - c. ☐ is not required, as the application was filed in the United States Receiving Office (RO/US).
6. ☒ An English language translation of the International Application as filed (35 U.S.C. 371(c)(2)).
 - a. ☒ is attached hereto.
 - b. ☐ has been previously submitted under 35 U.S.C. 154(d)(4).
7. ☐ Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371(c)(3))
 - a. ☐ are attached hereto (required only if not communicated by the International Bureau).
 - b. ☐ have been communicated by the International Bureau.
 - c. ☐ have not been made; however, the time limit for making such amendments has NOT expired.
 - d. ☐ have not been made and will not be made.
8. ☐ An English language translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371 (c)(3)).
9. ☒ An oath or declaration of the inventor(s) (35 U.S.C. 371(c)(4)).
10. ☐ An English language translation of the annexes of the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371(c)(5)).

Items 11 to 20 below concern document(s) or information included:

11. ☐ An Information Disclosure Statement under 37 CFR 1.97 and 1.98.
12. ☒ An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.
13. ☒ A **FIRST** preliminary amendment.
14. ☐ A **SECOND** or **SUBSEQUENT** preliminary amendment.
15. ☐ A substitute specification.
16. ☐ A change of power of attorney and/or address letter.
17. ☐ A computer-readable form of the sequence listing in accordance with PCT Rule 13ter.2 and 35 U.S.C. 1.821 - 1.825.
18. ☐ A second copy of the published international application under 35 U.S.C. 154(d)(4).
19. ☐ A second copy of the English language translation of the international application under 35 U.S.C. 154(d)(4).
20. ☒ Other items or information:

PTO FORM 1449 AND REFERENCES LISTED THEREIN; PRELIMINARY AMENDMENT W/ABSTRACT

U.S. APPLICATION NO. (if known) 09/807094 TO BE ASSIGNED	INTERNATIONAL APPLICATION NO PCT/EP99/07349	ATTORNEY'S DOCKET NUMBER Mo-6283/WW-5514
---	---	--

21. ☒ The following fees are submitted:

BASIC NATIONAL FEE (37 CFR 1.492 (a) (1) - (5)):

Neither international preliminary examination fee (37 CFR 1.482)
 nor international search fee (37 CFR 1.445(a) (2)) paid to USPTO
 and International Search Report not prepared by the EPO or JPO **\$1000.00**

International preliminary examination fee (37 CFR 1.482) not paid to
 USPTO but International Search Report prepared by the EPO or JPO **\$860.00**

International preliminary examination fee (37 CFR 1.482) not paid to USPTO
 but international search fee (37 CFR 1.445(a)(2)) paid to USPTO **\$710.00**

International preliminary examination fee (37 CFR 1.482) paid to USPTO
 but all claims did not satisfy provisions of PCT Article 33(1)-(4) **\$690.00**

International preliminary examination fee (37 CFR 1.482) paid to USPTO
 and all claims satisfied provisions of PCT Article 33(1)-(4) **\$100.00**

ENTER APPROPRIATE BASIC FEE AMOUNT =

CALCULATIONS PTO USE ONLY

\$ 860.00

Surcharge of **\$130.00** for furnishing the oath or declaration later than ☐ 20 ☐ 30
 months from the earliest claimed priority date (37 CFR 1.492(e)).

\$

CLAIMS	NUMBER FILED	NUMBER EXTRA	RATE	\$
Total claims	12 -20 =	0	x \$18.00	\$ 0.00
Independent claims	1 -3 =	0	x \$80.00	\$ 0.00
MULTIPLE DEPENDENT CLAIM(S) (if applicable)			+ \$270.00	\$ 0.00

TOTAL OF ABOVE CALCULATIONS =

\$ 860.00

☒ Applicant claims small entity status. See 37 CFR 1.27. The fees indicated above
 are reduced by 1/2.

+

0.00

SUBTOTAL =

\$ 860.00

Processing fee of **\$130.00** for furnishing the English translation later than ☐ 20 ☐ 30
 months from the earliest claimed priority date (37 CFR 1.492(f)).

\$

TOTAL NATIONAL FEE =

\$ 860.00

Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be
 accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31). **\$40.00** per property +

\$

40.00

TOTAL FEES ENCLOSED =

\$ 900.00

Amount to be
 refunded:

\$

charged:

\$

- a. ☐ A check in the amount of \$ _____ to cover the above fees is enclosed.
- b. ☒ Please charge my Deposit Account No. 13-3848 in the amount of \$ 900.00 to cover the above fees.
 A duplicate copy of this sheet is enclosed.
- c. ☒ The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any
 overpayment to Deposit Account No. 13-3848. A duplicate copy of this sheet is enclosed.
- d. ☐ Fees are to be charged to a credit card. **WARNING:** Information on this form may become public. **Credit card
 information should not be included on this form.** Provide credit card information and authorization on PTO-2038.

**NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR
 1.137 (a) or (b)) must be filed and granted to restore the application to pending status.**

SEND ALL CORRESPONDENCE TO

JAMES R. FRANKS
 BAYER CORPORATION
 PATENT DEPARTMENT
 100 BAYER ROAD
 PITTSBURGH, PA 15205-9741
 USA



00157

PATENT TRADEMARK OFFICE

James R. Franks
 SIGNATURE

JAMES R. FRANKS
 NAME

42,552
 REGISTRATION NUMBER

09/807094

JC02 Rec'd PCT/PTO 09 APR 2001

PATENT APPLICATION
Mo-6283
WW-5514

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

APPLICATION OF)
HOLGER EGGERS ET AL) PCT/EP99/07349
SERIAL NUMBER: TO BE ASSIGNED)
FILED: HEREWITH)
TITLE: HIGH LUSTER, FLEXIBLE)
MULTILAYERED FILM WITH A)
POLYAMIDE OUTER LAYER)
CONTAINING NANODISPERSED)
FILLING MATERIAL AND)
UTILIZATION OF SAID FILM FOR)
PACKAGING FOODSTUFFS)

PRELIMINARY AMENDMENT

Assistant Commissioner for Patents
Washington, D.C. 20231

Sir:


This preliminary amendment is being filed concurrently with the subject patent application. Upon granting a Serial Number and filing date, please amend the subject patent application as follows.

"Express Mail" mailing label number EK633383573US
Date of Deposit April 9, 2001

I hereby certify that this paper or fee is being deposited with the United States Postal Service "Express Mail Post Office to Addressee" service under 37 CFR 1.10 on the date indicated above and is addressed to the Assistant Commissioner of Patents and Trademarks, Washington, D.C. 20231

Donna J. Veatch

(Name of person mailing paper or fee)


Signature of person mailing paper or fee)

Please amend the Application as follows:

IN THE SPECIFICATION:

Please replace the title at the top of page 1 with the following
--HIGH LUSTER, FLEXIBLE MULTILAYERED FILM WITH A POLYAMIDE OUTER
LAYER CONTAINING NANODISPERSED FILLING MATERIAL AND UTILIZATION
OF SAID FILM FOR PACKAGING FOODSTUFFS--

IN THE ABSTRACT:

On a separate page, please add the following abstract.
--HIGH LUSTER, FLEXIBLE MULTILAYERED FILM WITH A POLYAMIDE OUTER
LAYER CONTAINING NANODISPERSED FILLING MATERIAL AND UTILIZATION
OF SAID FILM FOR PACKAGING FOODSTUFFS

ABSTRACT OF THE DISCLOSURE

Described is a flexible, multilayered film comprising, (i) an outer layer composed substantially of polyamide containing nanodispersed filling material (e.g., in an amount of from 0.1 and 3 wt. %), and (ii) at least one additional polyamide layer. The multilayered film of the present invention may be produced by flat film or blown film methods. Also described is a method of using the multilayered film of the present invention as a packaging for foodstuffs.--

A separate abstract page is included herewith.

IN THE CLAIMS:

Please replace Claim 2 with the following:

2. (Once Amended, Clean) The multilayer film of Claim 1 wherein the proportion by weight of the particles dispersed in the outer layer, relative to the total weight of the composition forming the outer layer, is between 0.1 and 3 wt. %.

Please replace Claim 3 with the following:

3. (Once Amended, Clean) The multilayer film of Claim 1 wherein in addition to polyamide 6, the outer layer contains a polyamide selected from the group comprising polyamide 6, polyamide 10, polyamide 12, polyamide 66, polyamide 610, polyamide 6I, polyamide 612, polyamide 6/66, polyamide 6I/6T, polyamide MXD6, polyamide 6/6I, polyamide 6/6T, polyamide 6/IPDI, copolymers of monomers forming said polymers or mixtures of said polymers or copolymers.

Please replace Claim 4 with the following:

4. (Once Amended, Clean) The multilayer film of Claim 1 wherein the particles dispersed in the outer layer comprise particles that have, in two mutually perpendicular directions that can be arbitrarily chosen for each particle, a dimension in each case of at least a tenth of the dimension of the particles in the direction with the smallest dimension.

Please replace Claim 5 with the following:

5. (Once Amended, Clean) The multilayer film of Claim 1 wherein the particles dispersed in the outer layer are sheet silicates.

Please replace Claim 6 with the following:

6. (Once Amended, Clean) The multilayer film of Claim 1 wherein said multilayer film contains one or more EVOH-containing layers.

Please replace Claim 7 with the following:

7. (Once Amended, Clean) The multilayer film of Claim 1 wherein said multilayer film has an at least monolayer heat-sealable coating on that side of the multilayer film remote from the outer layer.

Please replace Claim 8 with the following:

8. (Once Amended, Clean) The multilayer film of Claim 1 wherein said multilayer film contains one or more coupling layers.

Please replace Claim 9 with the following:

9. (Once Amended, Clean) The multilayer film of Claim 1 wherein in addition to the outer layer and one or more further layers composed of polyamide and, optionally, conventional additives and also, optionally, one or more EVOH-containing layers, one or more heat-sealable coatings and also one or more coupling layers, said multilayer film additionally contains one or more further polymeric layers or a layer of a metal oxide or nonmetal oxide between two inner layers.

Please replace Claim 10 with the following:

10. (Once Amended, Clean) The multilayer film of Claim 1 wherein at least one outer layer, optionally also a plurality of or all the layers are subjected after extrusion to a stretching operation selected from: stretching only in the longitudinal direction; stretching only in the transverse direction; stretching first in the longitudinal direction and then in the transverse direction; stretching simultaneously in the longitudinal direction and transverse direction; and combinations thereof.

Please replace Claim 11 with the following:

11. (Once Amended, Clean) The multilayer film of Claim 1 wherein said multilayer film is produced as a blown film by coextrusion.

Please replace Claim 12 with the following:

12. (Once Amended, Clean) A method of using the multilayer film of Claim 1 for packaging foodstuffs.

REMARKS

Claims in the case are 1 to 12. Claims 2 to 12 have been amended herein.

Claims 2 to 12 of the above-identified patent application have been amended as to form, for example, replacing "characterized in that" with --wherein--, and converting multi-dependent claims to dependent claims. The patent application has also been amended to include an abstract on a separate page, which is included herewith. The amendments presented herein do not represent the entry of new matter into the application. Applicants respectfully request entry of this amendment.

Respectfully submitted,

HOLGER EGGERS
GREGOR KASCHEL

By James R. Franks
James R. Franks
Agent for Applicants
Reg. No. 42,552

Bayer Corporation
100 Bayer Road
Pittsburgh, Pennsylvania 15205-9741
(412) 777-2905
FACSIMILE PHONE NUMBER:
(412) 777-5449

s:/sr/jrf0035

VERSIONS WITH MARKINGS TO SHOW CHANGES MADE

IN THE SPECIFICATION: (Marked-Up)

The following is a version of the title at the top of page 1, with markings to show changes made thereto in the present Preliminary Amendment.

[High-gloss, flexible multilayer film having a polyamide outer layer containing nanodisperse filler and its use for packaging foodstuffs]

HIGH LUSTER, FLEXIBLE MULTILAYERED FILM WITH A POLYAMIDE OUTER LAYER CONTAINING NANODISPERSED FILLING MATERIAL AND UTILIZATION OF SAID FILM FOR PACKAGING FOODSTUFFS

IN THE CLAIMS: (Marked-Up)

The following are versions of the amended claims with markings to show changes made thereto in the present Preliminary Amendment.

2. (Once Amended, Marked-Up) The [M]multilayer film [according to] of Claim 1[, characterized in that] wherein the proportion by weight of the particles dispersed in the outer layer, relative to the total weight of the composition forming the outer layer, is between 0.1 and 3 wt. %.[.]

3. (Once Amended, Marked-Up) The [M]multilayer film [according to] of Claim 1 [or 2, characterized in that,] wherein in addition to polyamide 6, the outer layer contains a polyamide selected from the group comprising polyamide 6, polyamide 10, polyamide 12, polyamide 66, polyamide 610, polyamide 6I, polyamide 612, polyamide 6/66, polyamide 6I/6T, polyamide MXD6, polyamide 6/6I, polyamide 6/6T, polyamide 6/IPDI, copolymers of monomers forming said polymers or mixtures of said polymers or copolymers.

4. (Once Amended, Marked-Up) The [M]multilayer film [according to one] of Claim[s] 1 [to 3, characterized in that] wherein the particles dispersed in the outer layer comprise particles that have, in two mutually perpendicular directions that can

be arbitrarily chosen for each particle, a dimension in each case of at least a tenth of the dimension of the particles in the direction with the smallest dimension.

5. (Once Amended, Marked-Up) The [M]multilayer film [according to one] of Claim[s] 1 [to 4, characterized in that] wherein the particles dispersed in the outer layer are sheet silicates.

6. (Once Amended, Marked-Up) The [M]multilayer film [according to one] of Claim[s] 1 [to 5, characterized in that it] wherein said multilayer film contains one or more EVOH-containing layers.

7. (Once Amended, Marked-Up) The [M]multilayer film [according to one] of Claim[s] 1 [to 6, characterized in that it] wherein said multilayer film has an at least monolayer heat-sealable coating on that side of the multilayer film remote from the outer layer.

8. (Once Amended, Marked-Up) The [M]multilayer film [according to one] of Claim[s] 1 [to 7, characterized in that it] wherein said multilayer film contains one or more coupling layers.

9. (Once Amended, Marked-Up) The [M]multilayer film [according to one] of Claim[s] 1 [to 8, characterized in that,] wherein in addition to the outer layer and one or more further layers composed of polyamide and, optionally, conventional additives and also, optionally, one or more EVOH-containing layers, one or more heat-sealable coatings and also one or more coupling layers, [it] said multilayer film additionally contains one or more further polymeric layers or a layer of a metal oxide or nonmetal oxide between two inner layers.

10. (Once Amended, Marked-Up) The [M]multilayer film [according to one] of Claim[s] 1 [to 9, characterized in that] wherein at least one outer layer, optionally

also a plurality of or all the layers are subjected after extrusion to a stretching operation selected from: stretching only in the longitudinal direction[,]; stretching only in the transverse direction[,]; stretching first in the longitudinal direction and then in the transverse direction[,]; stretching simultaneously in the longitudinal direction and transverse direction; [or] and combinations thereof.

11. (Once Amended, Marked-Up) The [M]multilayer film [according to one] of Claim[s] 1 [to 10, characterized in that it] wherein said multilayer film is produced as a blown film by coextrusion.

12. (Once Amended, Marked-Up) [Use of a] A method of using the multilayer film [according to one] of Claim[s] 1 [to 13] for packaging foodstuffs.

High-gloss, flexible multilayer film having a polyamide outer layer containing nanodisperse filler and its use for packaging foodstuffs

5 The present invention relates to a flexible, multilayer film having an outer layer composed essentially of polyamide 6 that contains between 0.1 and 3.0% of a nanodisperse nucleating agent, and at least one further polyamide layer. The multilayer film according to the invention is notable for good optical properties accompanied by high strength and good slip. The multilayer film can be produced without difficulty, in particular on blown-film plants. The multilayer film can be

10 processed without difficulty using a suitable heat-sealable coating on modern moulding, filling and sealing packaging machines at high packing speeds. The packages produced are optically attractive and resistant to mechanical stress. The invention also comprises the use of the multilayer film according to the invention as a container, in particular for the packaging of foodstuffs, and also the use as

15 thermoformed film. In the context of the present invention, a nanodisperse filler is understood in this connection as meaning a filler whose smallest particles that form a rigid unit in the dispersion have a dimension of not more than 100 nm as a number-weighted average of all the particles in at least one direction that can be chosen arbitrarily for each particle.

20

Polyamide-based films are by far predominantly used to package perishable foodstuffs. The structure of suitable films is set out, for example, in The Wiley Encyclopedia of Packaging Technology (ed. M. Bakker and D. Eckroth; John Wiley & Sons, 1986) and also in Kunststoff-Folien by Joachim Nentwig (Carl Hanser Verlag 1994, Munich).

As barrier layer material in flexible multilayer films or composite films, usually in combination with low-density polyethylene (LDPE), polyamides have acquired increasing importance for packaging perishable foodstuffs over many years. In this field, polyamide 6 (PA 6) has acquired the greatest share. The annual consumption of PA 6 for this market is currently around 35,000 tonnes in Europe and about

EK633835/3US

April 9, 2001

"Express Mail" mailing label number

Date of Deposit

I hereby certify that this paper or fee is being deposited with the United States Postal Service "Express Mail Post Office to Addressee" service under 37 CFR 1.10 on the date indicated above and is addressed to the Assistant Commissioner of Patents and Trademarks, Washington, D.C. 20231

Donna J. Veatch

(Name of person mailing paper or fee)

Signature of person mailing paper or fee

- 2 -

85,000 tonnes world-wide; in addition, a few thousand tonnes of copolyamides are used.

5 By far the largest quantity of said multilayer films is produced using PA 6 types in various flat-film processes. For blown-film composites, special copolyamides are usually used.

10 Copolyamides are almost exclusively processed by the blown-film coextrusion process. Their solidification rate or crystallization rate during the cooling phase is markedly slower than pure PA 6 products. As a result, despite the relatively low cooling rate of the molten tube through air cooling, it is possible to produce PA/PE composite films having a high transparency. The copolyamides that are conventional in this connection are nowadays also partly used with various modifications, such as nucleation agents and processing aids, for example an asymmetrical PE-X-PA blown
15 coextrusion film (X = coupling agent) for the PA outer layer to improve free running in machines and dimensional stability. Small losses in transparency due to the crystallizing action of the nucleating agents are, as a rule, accepted because of the other advantages.

20 In many cases, films are necessary that have been produced as blown film. An advantage of a blown film is the better uniformity of the film roll compared with flat films as the result of a changing take-up. As a result, the blown film is given a flatness that is markedly superior to a flat film. This is advantageous for fast machine running.

25 According to the prior art, an outer polyamide layer is used because of the outstanding thermal stability and abrasion resistance.

30 The disadvantages that increase as a result of the use of copolyamides reside in the post-crystallization of the film. Because of the low crystallization rate of these systems, the crystallization is still not complete with the actual forming. On the contrary, subsequent to the actual production of the film, a post-crystallization takes

place over a fairly long time interval, as a result of which, due to the dimensional change in the polyamide-containing film accompanying the post-crystallization, the multilayer film may curl up and/or may shrink considerably, resulting in flatness deficiencies on the roll, and is consequently no longer suitable for further processing.

In addition, because of the lower crystallinity compared with PA 6, copolyamides have the disadvantage of a markedly poorer surface slip. This is relevant in the case of the outer polyamide.

Not least of all, the production of the copolyamides even requires the use of more expensive raw materials and polymerization procedures than the production of PA 6. In this respect, the use of copolyamides results in an even greater consumption of resources.

In this respect, there is a need, not covered at present, for blown films having a polyamide outer layer that have both good optical properties and good machine free running in the context of good surface slip. The best existing solution in the prior art is to use nucleated copolyamide. However, compared with the use of polyamide 6, this solution has a marked disadvantage because of the more exotic and expensive copolyamide raw material.

A further important property is a high mechanical resistance. This relates, in particular, to a high resistance to destruction as a result of buckling and bending, referred to below as loop strength, and also a high resistance to puncture by sharp objects, referred to below as puncture strength.

Nucleating agents, such as the systems mentioned above for use in copolyamides, have been prior art for a fairly long time. They also serve as crystallization nuclei during slight supercooling of the melt around which spherulitic structures form during the solidification process. Depending on dispersion and effectiveness, such nucleating agents achieve, in this way, the development of a crystal structure

containing more and finer spherulites than in the unnucleated polymer, even in the case of slow cooling from the melt, as in the case of blown-film production. Post-shrinking as a result of post-crystallization can thereby be minimized. The loading of the moulding composition with nucleating agents is, however, restricted by the light-scattering properties of the nucleating agents themselves.

The addition of very fine-grain solid particles in the size range below one micrometre to polymeric matrices and especially polyamides has likewise been described for a fairly long time. Such systems are primarily used to increase the mechanical rigidity, the barrier to gases and the heat resistance, and also to reduce the cycle time, for instance, during injection moulding, the flammability or the moisture absorption in the case of hydrophilic systems. Systems that, in contrast to the abovementioned nucleated polyamides, retain their transparency despite greater additions of nanoscale particles have also been described.

EP-A-358415 describes a polyamide resin moulding composition containing sheet silicate uniformly dispersed in it, in which the individual layers of the sheet silicate may have thicknesses around 1 nm and side lengths of up to 1 μm . The layers are separated in the polyamide matrix by suitable breakdown and are at distances from one another of around 10 nm. Mouldings, such as, for example, films, produced with this material composed of polyamide 6 as base polymer are notable, compared with those of pure polyamide 6, for a significantly increased oxygen barrier and rigidity. To an equal extent, however, the loop strength decreases markedly. The transparency of single-layer amorphously quenched flat films and also water-cooled blown films having the structure polyamide mixture//coupling agent//LDPE remains unaltered compared with pure polyamide 6. Consequently, the structures used do not achieve the necessary property profile for the present application.

WO 93 04118 and WO 93 11190 and WO 93 04117 disclose polymer nanocomposites containing likewise platelet-shaped particles in the thickness range of a few nanometres. In particular, composites are described that are composed of PA 6 and montmorillonite or of PA 6 and silicates. These materials can be processed

to form films. Applications as monofilms and the possibility of producing multilayer films are described. In these cases, the films made from said material can optionally be stretched in order to achieve a still better orientation of the nanoparticles. Compared with those not containing nanoscale particles, such films exhibit a higher rigidity, a higher strength in the moist state, a better dimensional stability, a higher gas barrier and a lower water absorption. Such film structures are unsuitable for the present application case because of the unduly high rigidity and the low loop strength accompanying it.

EP-A-818508 discloses a mixture of 60 to 98% PA MXD6 containing 2 to 40% of an aliphatic polyamide that again contains inorganic particles in the size range of nanometres. Mixtures are described that contain, in particular, PA 6 as aliphatic polyamide. In addition, multilayer films are described as mouldings producible therefrom. Disclosed structures always contain the mixture described as an inner and/or outer layer. Structures containing the said layer and a layer that is situated on the outside of the film with PA 6 containing nanoparticles are also described. All the structures mentioned have as an advantage a high oxygen barrier that is not impaired even by sterilization. In contrast to films having EVOH as oxygen barrier layer, the films patented therein become only slightly cloudy as a result of the sterilization. Compared with a flat film composed of pure PA 6, such a film having the structure PA 6/(80% PA MXD6 + 20% PA containing nanoparticles)// PA 6 do not exhibit any appreciable improvement in transparency. Such structures containing a high proportion of PA MXD6 are unsuitable for the present application case simply because of the low loop strength of this material.

EP-A- 810259 likewise describes a polyamide moulding composition containing nanodisperse fillers. The barrier action, desired therein, of the polyamide can be improved by adding sufficient finely-divided oxides, oxyhydrates or carbonates. Preferably, the particles have a diameter of less than 100 nm. The Patent also describes multilayer films containing at least one layer composed of this moulding composition, an improvement in the oxygen barrier always being the intention of using said moulding composition. The optical properties of the films moulded

therefrom become poorer, however, compared with the system without additives. Such a system is therefore unsuitable for the present requirements.

5 WO 98 1346 likewise describes the use of nanodisperse fillers for improving the barrier properties of polymers. The publication especially discloses the constitution of a transparent multilayer structure whose outer layer contains a polymer having a proportion of between 0.1 and 10% of a dispersed platelet-shaped mineral and having a particle thickness of less than 100 nm dispersed within it, said outer layer being coated with a metal oxide on the side facing the centre of the structure. This is
10 followed by a coupling layer and a further layer that serves as heat-sealable coating and that is preferably composed of polyolefins. The polymer of the outer layer may be a polyester or a polyamide. The structure has a high oxygen barrier and strength, accompanied by the retention of the transparency, and is used, for example, to produce tubular bags. In this case, said structure comprises only the outer layer
15 containing the nanodisperse mineral as strengthening layer. Such a structure, but without metal oxide layer, proves unsuitable for the present application case because the film acquires a markedly higher rigidity as the result of the addition of the nanodisperse fillers, but becomes brittle to an equal extent and consequently markedly fails to meet, in particular, the requirements relating to loop strength.

20 The object arose of providing a flexible multilayer film that can be produced as a blown film and that has an outer layer essentially composed of polyamide 6, which layer has a high gloss and a high transparency for the optimum presentation of the contents, it being essential for it to have not only a good processability on packaging
25 machines but also an adequate loop strength and puncture strength to protect the contents.

According to the invention, this was achieved by providing a multilayer film optionally having a heat-sealable coating and having a polyamide outer layer
30 containing nanoscale particulate nucleating agents and at least one further polyamide layer, wherein

the polyamide forming the outer layer contains at least 90% polyamide 6, relative to the total mass of polyamide in said layer,

the smallest constituents, forming a rigid unit in the dispersion, of the particles dispersed in the outer layer have as a number-weighted average of all the constituents a dimension of not more than 100 nm in at least one direction that can be arbitrarily chosen for each constituent,

during cooling of the outer layer from the completely molten state at a cooling rate of between 10° and 20°C per minute, crystalline structures are produced that originate from the surface of the particles dispersed therein,

all the further polyamide layers contain the particles contained in the outer layer at a level of not more than one tenth of the proportion by weight of particles in the outer layer,

and the thickness of the outer layer is less than 50% of the total thickness of all the layers containing polyamide.

Preferably, the proportion by weight of the particles dispersed in the outer layer, relative to the total weight of the composition forming the outer layer, is between 0.1 and 3%, preferably between 0.2 and 2.0%.

The polyamide forming the outer layer may contain, in addition to polyamide 6, polyamide of the types polyamide 10, polyamide 12, polyamide 66, polyamide 610, polyamide 6I, polyamide 612, polyamide 6/66, polyamide 6I/6T, polyamide MXD6, polyamide 6/6I, polyamide 6/6T, polyamide 6/IPDI or other aliphatic or aromatic homopolyamides and copolyamides or mixtures thereof. Preferably, the outer layer contains pure polyamide 6. Unduly high added amounts of other polyamides impair, in particular, the surface slip characteristics of the film.

The further layers, apart from the outer layer, composed of polyamide may in each case contain polyamide of the types polyamide 6, polyamide 10, polyamide 12, polyamide 66, polyamide 610, polyamide 6I, polyamide 612, polyamide 6/66, polyamide 6I/6T, polyamide MXD6, polyamide 6/6I, polyamide 6/6T, polyamide 5 6/IPDI or other aliphatic or aromatic homopolyamides and copolyamides or mixtures thereof. In a preferred form, mixtures of the said polyamides are used that contain at least 80 wt % of polyamide 6, relative to the total weight of the mixture. Particularly preferred is the use of pure polyamide 6 in said layers.

10 It is basically also possible to provide the further layers, apart from the outer layer, composed of polyamide with dispersed particles, as in the outer layer.

The layers composed of polyamide in the film according to the invention may also contain conventional further additives that improve the functionality of the film, 15 such as lubricants, in particular ethylenebis(stearyl)amide. In addition, the outer layer may contain antiblocking agents. These are known solid inorganic particles that emerge from the outer surface of the surface and improve the surface slip behaviour of the film in this way. Suitable for this purpose are silicon oxide, calcium carbonate, magnesium silicate, aluminium silicate, calcium phosphate, talcum and 20 the like. Of these, silicon dioxide is preferably used. Active amounts are in the range from 0.1 to 2 wt %, preferably 0.1 to 0.8 wt %. The mean particle size is between 1 and 15 µm, particles that have a spherical shape being particularly suitable in this connection.

25 The thickness of the outer layer is preferably not more than 40% of the total thickness of all the layers containing polyamide. Unduly high thicknesses of the layer (I) result in a multilayer film that is too brittle.

30 Preferably, particles whose smallest constituents forming a rigid unit in the dispersion have, in two mutually perpendicular, arbitrarily directions that can be chosen arbitrarily, a dimension in each case of at least ten times the size of the constituents in the direction with the smallest dimension of the constituent. The

thickness of said particles is preferably less than 10 nm. The particles used in the outer layer are preferably sheet silicate. These may be selected from the group comprising phyllosilicates, such as magnesium silicate or aluminium silicate, and also montmorillonite, saponite, beidellite, nontronite, hectorite, stevensite, vermiculite, halloysite or their synthetic analogues.

To promote the heat sealability, the multilayer film according to the invention may have a heat-sealable coating on that side of the multilayer film that is remote from the outer layer. The heat-sealable coating consequently forms the inside of the multilayer film, which is adjacent to the contents. In a preferred form, the heat-sealable coating contains the polymers usually used as sealing medium or mixtures of polymers from the group comprising copolymers of ethylene and vinyl acetate (E/VA), particularly preferably having a vinyl acetate content, relative to the total weight of the polymer, of not more than 20%, copolymers of ethylene and unsaturated esters, such as butyl acrylate or ethyl acrylate (E/BA or E/EA, respectively), copolymers of ethylene and unsaturated carboxylic acids (E/AA, E/MAA), particularly preferably having a content of the carboxylic acid comonomer, relative to the total weight of the polymer, of not more than 15%, in a still more preferred form of not more than 8%, salts of the copolymers of ethylene and unsaturated carboxylic acids, in particular E/MAA, (ionomers), particularly preferably having a content of the carboxylic acid comonomers, relative to the total weight of the ionomer, of not more than 15%, in a still more preferred form, not more than 10%, low-density polyethylene (LDPE), particularly preferably with a density of not less than 0.91 g/cm³ and not more than 0.935 g/cm³, high-density polyethylene (HDPE), copolymers (LLDPE) of ethylene and α -olefins containing at least 3 carbon atoms, for example butene, hexene, octene, 4-methyl-1-pentene. The copolymers (LLDPE) of ethylene and α -olefins can be prepared using conventional catalysts or with metallocene catalysts. Particularly preferred among the latter are copolymers (LLDPE) of ethylene and α -olefins having a density of not less than 0.90 g/cm³ and not more than 0.94 g/cm³.

The film according to the invention may also contain a heat-sealable coating of multilayer construction. Thus, the abovementioned polymers may be arranged, for instance for cost optimization, in such a way that the individual layer situated on the inside of the film and adjacent to the product may be notable for a particularly early start of sealing and the individual layer adjacent to the middle of the film thereon only melts at higher temperatures, but, on the other hand, is less expensive or only makes possible the producibility of such a multilayer heat-sealing coating as a blown film as a result of higher resistance to melting. In the heat-sealable coating, coupling polymers composed of the said substance groups or polymers produced on the basis of them, modified, for instance, with anhydride by grafting may also be used. Examples of such structures are the film sequences LDPE//E//VA or LDPE//E//AA//ionomer.

All the layers or individual layers of the heat-sealable coating may additionally be provided with additives that improve the functionality of the film. Examples are solid inorganic particles that are known as antiblocking agents and that emerge from the outer surface of the heat-sealable coating and improve the surface slip behaviour of the film in this way. Suitable for this purpose are silicon oxide, calcium carbonate, magnesium silicate, aluminium silicate, calcium phosphate, talcum and the like. Of these, silicon dioxide is preferably used. Active amounts are in the range from 0.1 to 2 wt %, preferably 0.1 to 0.8 wt %. The mean particle size is between 1 and 10 μm , preferably 2 and 5 μm , particles having a spherical shape being particularly suitable in this connection. In multilayer heat-sealable coatings, said particles are preferably used only in the outer individual layer. Other additives that improve the surface slip of the inside of the multilayer film, also in conjunction with the said solid particles, are the aliphatic acid amides, higher aliphatic acid esters, waxes, metal soaps and polydimethylsiloxanes that are usually described as lubricants. The active amount of lubricant is in the range of 0.01 to 3 wt %, preferably 0.02 to 1 wt %. Particularly suitable is the addition of higher aliphatic acid amides in the range from 0.01 to 0.25 wt %. An aliphatic acid amide that is suitable, in particular, for the abovementioned polymers used in the heat-sealable coating is erucic amide.

In addition to the outer polyamide layer and, optionally, conventional additives and at least one further polyamide layer and, optionally, conventional additives and the heat-sealable coating, the multilayer film according to the invention may also contain one or more EVOH-containing layers to improve the oxygen barrier properties, in which connection the EVOH-containing layers preferably contain not less than 50 wt %, relative to the total weight of the respective EVOH-containing layer, of an EVOH containing not less than 85 and not more than 40 mol % of vinyl acetate that is not less than 90% saponified. In a particularly preferred form, an EVOH-containing layer is disposed directly between two polyamide-containing layers, of which one may be the outer layer.

In addition to the polyamide outer layer and, optionally, conventional additives and at least one further polyamide layer and, optionally, conventional additives and, optionally, the EVOH-containing layer or layers and the heat-sealable coating, the film according to the invention may contain one or more coupling layers. Such a coupling layer is preferably a laminating adhesive based on polyurethane or polyester urethanes or an extrudable coupling agent. Modified polyolefins are preferably used as an extrudable coupling agent. In a preferred form, these are polyolefins containing carboxyl groups, such as, for example, polyethylene, polypropylene, ethylene/ α -olefin copolymers or ethylene/vinyl acetate copolymers that are grafted with at least one monomer from the group comprising the α,β -monounsaturated dicarboxylic acids, such as, for example, maleic acid, fumaric acid, itaconic acid or their acid anhydrides, acid esters, acid amides and acid imides. In addition, copolymers of ethylene with α,β -monounsaturated dicarboxylic acids, such as acrylic acid, methacrylic acid and/or their metal salts with zinc or sodium and/or their alkyl (C_1 - C_4)ester or corresponding graft polymers on polyolefins, such as, for example, polyethylene, polypropylene or ethylene/ α -olefin copolymers that are graft-polymerized with a monomer of the said unsaturated acids are used as extrudable coupling agents. Particularly preferred are polyolefins with grafted α,β -monounsaturated dicarboxylic anhydride, in particular ethylene/ α -olefin copolymers grafted with maleic anhydride. In general, the layers joined by a

coupling agent do not have sufficiently high mutual adhesion. However, coupling agent layers may also be used between two directly coextrudable layers in order to modify, for instance, the flexibility of the film.

- 5 In addition to the polyamide outer layer and, optionally, conventional additives and at least one further polyamide layer and, optionally, conventional additives, optionally, the EVOH-containing layer or layers and the heat-sealable coating and/or one or more coupling layers, it is basically also possible to provide the multiplayer film according to the invention with an inner layer whose composition is identical to
10 that of the outer layer. Such a procedure does not, however, present any advantages with regard to the properties desired in the context of the object.

- In addition to the polyamide outer layer and, optionally, conventional additives and at least one further polyamide layer and, optionally, conventional additives,
15 optionally the EVOH layer or layers and the heat-sealable coating and/or one or more coupling layers, the multilayer film according to the invention may contain still other polymeric layers.

- The multilayer film according to the invention may also be subjected to a stretching operation after extrusion. The orientation may take place only in the longitudinal direction, only in the transverse direction, first in the longitudinal direction and then in the transverse direction, simultaneously in the longitudinal and transverse directions or in combinations of these steps. In this connection, the stretching can be performed for the entire multilayer film or for subcomposites thereof, in particular
20 the outer layer.
25

- The multilayer film according to the invention may be provided between two inner layers containing a layer of a metal oxide or nonmetal oxide, represented as AO_x . Said layer preferably has a thickness of 5 to 200 nm. In the empirical formula
30 mentioned, x is between 1 and 2.5; A is preferably silicon, iron or aluminium.

The film according to the invention may be given an imprint on the outside, the inside or between individual layers.

5 Surprisingly, the film according to the invention makes it possible to provide a blown film having an outer PA layer and good optical properties without using copolyamides.

10 The multilayer film according to the invention thereby overcomes a disadvantage generally accepted by those skilled in the art for coextruded blown films.

15 The film according to the invention consequently makes it possible to minimize the use of raw materials, such as copolyamides, that are more costly to produce. This makes possible a resource-saving manufacture of the film according to the invention, compared with the prior art.

20 It was not to be expected that the film acquires, in addition, also good mechanical flexibility, accompanied by loop strength and puncture strength, as a result of the multilayer structure.

25 The optical properties of the multilayer film according to the invention are far superior to those of conventionally nucleated films.

The object of the invention is also the use of the multilayer film according to the invention for the preferably mechanized packaging of foodstuffs, in particular for the production of bags on tubular bag machines and also as blister film and cover film in thermoform packaging and sealing machines.

Examples

In the case of multilayer structures, the layer sequence is shown by stringing together the abbreviations for the polymers of the respective layers or symbols explained elsewhere, mutually separated by double oblique strokes. In this connection, the heat-sealable coating side is always on the right. At the same time, only a part of the entire layer sequence forming the film can also be specified. In such cases, the heat-sealable coating side is likewise always on the right and unspecified layers or combinations of layers are identified by three stops (...).

Mixtures of different polymers are identified by the symbol + and also the summary of the components in brackets, (). Optionally, percentage composition can additionally be specified in this connection. Unless otherwise specified, in such cases, this always involves proportions by weight relative to the total weight of the mixture. Thus, the expression ...//PA//EVOH//...//(LDPE+LLDPE)//d describes a structure having an unspecified outer layer or outer layer sequence, followed by a layer composed essentially of polyamide, followed by a layer composed essentially of ethylene-vinyl alcohol copolymer (EVOH), followed by an unspecified layer or layer sequence, followed by a layer that comprises a mixture of low density polyethylene (LDPE) and an ethylene/ α -olefin copolymer (LLDPE), and also a layer to be specified in greater detail by d that follows on the sealing side.

The following physical and application properties were measured on the samples manufactured as follows:

- 25 - The frictional behaviour according to DIN 53 375. The frictional coefficients are measured for the static friction between film and film. It is always the polyamide outside of the exemplary film that is investigated. The measurement was carried out at 23°C.
- 30 - The puncture strength as the necessary force, the necessary travel and the necessary work to puncture a film stretched in membrane fashion with a sharp test mandrel from the seal side. In this connection, the puncture work is

- 15 -

found by experience to be best suited to assessing the strength with respect to sharp objects in practice. The measurement is made with an electronic class 1 tensile test machine according to DIN 51 221 at a test speed of 100 mm/min. For this purpose, circular samples having a diameter of 80 mm are taken from the film and clamped in membrane fashion in the specimen holder of the test apparatus having a diameter of 50 mm. The test mandrel is made of metal and has a diameter of 2 mm. At its tip, it tapers over a length of 5 mm to a diameter of 1 mm, the front part being rounded with a radius of 0.5 mm. The puncture work is given by integrating the force acting on the test mandrel over the path it traverses until the film fails. All the investigation steps were performed at 23°C and 50% relative atmospheric humidity. The tests were each performed on three samples and the results were averaged.

- The loop strength at a temperature of 23°C and a relative humidity of 50% by rolling up a specimen blank in a single layer to form a cylinder 198 mm long having a diameter of 280 mm and clamping it at both ends into suitably shaped holders. The unsupported length of the cylinder formed by the film between the holders is 192 mm while simultaneously rotating them through 440° around the symmetry axis describing the cylinder, the holders are moved towards one another to a distance of 40 mm with a given number of cycles and a frequency of 35 cycles per minute. The films to be tested are kept in a climate of 23°C and 50% relative atmospheric humidity for 7 days beforehand. The number of buckling breaks produced in this way in the film after a specified number of strokes can be determined by wetting the film with ammonia solution with simultaneous contact of the other side of the film with a sheet of diazo paper. The number of blue-black spots on the diazo paper produced by the ammonia and detectable after 15 min is assigned to the number of buckling breaks in the film portion investigated. In this case, the value is obtained as the average of the individual values of two test samples.

- The cloudiness according to ASTM D 1003.

- 16 -

- The gloss on the polyamide outside of the film at an angle of 20° according to DIN 67530.
- 5 - The producibility as a blown film under the specified conditions. In particular, the fold formation of the film when laid flat was assessed. The categories producible (yes) and not producible (no) were distinguished.
- 10 - The shrinkage of the film as a measure of the dimensional stability as the decrease in width, relative to the original width of the film, of the outermost layer of the finished film roll after three-week storage at 23°C and 50% relative humidity.

Test Series 1:

- 15 Three-layer coextruded blown films were manufactured with different polyamide compositions in the outer layer.

Comparison Example 1.1 (C1.1):

- 20 A film having the structure PA-1//HV//LDPE in the thicknesses 40//10//150 µm is produced as blown film by the conventional method for the production of blown films. The temperature of the cooling air is 20°C. The nozzle has a diameter of 300 mm and the film is laid flat over a width of 720 mm and then cut to a width of 700 mm. The parison was not, however, laid out on the winding mandrel. Immediately
- 25 after cutting, the parison halves are separated and the film is wound up. The output rate of the nozzle is 100 kg/h. The PA-containing layer forms the outside of the film parison.

- 30 PA-1 is a polyamide 6 containing 600 ppm of ethylenebis(stearyl)amide and is nucleated with approximately 150 ppm of talcum.

The coupling agent is an LLDPE grafted with maleic anhydride having a density of 920 kg/m³ and an MFI of 2.7 g/10 min measured at 190°C with an applied weight of 2.16 kg. A material having a density of 928 kg/m³ and an MFI of 1 g/min measure at 190°C with an applied weight of 2.16 kg.

5

Comparison Example 1.2 (C1.2):

The film from Comparison Example 1.1 is manufactured with the structure PA-2//HV//LDPE by the method and also with the same layer thicknesses, the same coupling agent and LDPE as in Comparison Example 1. PA-2 is a polyamide 6 containing 2 wt % of montmorillonite. The montmorillonite is present in dispersed form as platelets as a result of suitable digestion. The platelets have a thickness of approximately 1 nm and a diameter of 100 to 1000 nm.

10

Comparison Example 1.3 (C1.3):

15

The film from Comparison Example 1.1 is manufactured with the structure PA-3//HV//LDPE by the method and with the same layer thicknesses, the same coupling agent and LDPE as in Comparison Example 1. PA-3 is a copolyamide of the type PA6/IPDI having a melting point of 210°C. It is not nucleated. The copolyamide is additionally provided with 2000 ppm of a synthetic silicon dioxide as antiblocking agent. The silicon dioxide used has a particle diameter of approximately 8 µm.

20

The table below lists the properties measured on the three-layer films of Test Series 1:

Feature (unit)	Example (B) or Comparison Example (C) Structure PA//HV//LDPE, 40//10//150 µm		
	C1.1	C1.2	C1.3
Polyamide	PA6	PA6 containing 2 % montmorillonite	PA6/IPDI
Gloss (gloss units)	51	91	83
Cloudiness (%)	22	12	14
Number of holes after 250 strokes	6	13.5	3
Puncture work (N cm)	1.1	0.8	1.2
Coefficient of static friction for film/film at 23°C (-)	0.31	0.37	1.6
Shrinkage after production (%)	0.5	0.3	1.4
Producibility	yes	no*	yes

5 Table: Properties of films from Test Series 1.

It can be seen that good optical properties are obtained in the form of gloss and cloudiness by using a copolyamide (C1.3) in the outer layer. However, this film is found to have low surface slip and post-shrinks considerably on the roll. The use of
 10 pure polyamide 6 in the outer layer results in an optically unattractive film, whereas, although outer polyamide containing 2 % nanoscale dispersed sheet silicate produces an optically attractive film that does not post-shrink, it has too low a loop strength and puncture strength.

15 All the films of Test Series 1 do not fulfil the requirements of the object set here.

Test Series 2:

Three-layer and five-layer films having an outer layer of polyamide 6 with 2% nanoscale sheet silicate dispersed in it were produced.

5

Comparison Example 2.1:

Identical to Comparison Example 1.2.

10 **Comparison Example 2.2 (C2.2):**

A film having the structure PA-2//HV//PA-1//HV//LDPE is produced with the thicknesses 20//10//20//10//140 μm as blown film by the method and with the same coupling agent and LDPE as in Comparison Example 1.1. PA-2 is the polyamide from Comparison Example 1.2 and PA-1 is the polyamide from Comparison Example 1.1.

15

Example 2.3 (E2.3):

Film as in Comparison Example 2.2, but with the layer thicknesses 5//10//35//10//140 μm .

20

Comparison Example 2.4 (C2.4):

Film as in Comparison Example 2.2 having the structure PA-2//HV//PA-2//HV//LDPE.

25

T06010" 16020360

The table below lists the properties measured on the three-layer and five-layer films of Test Series 2:

Feature (unit)	Example (E) or Comparison Example (C) Structure PA*//HV//PA//HV//LDPE or PA*//HV//LDPE PA* = PA6 containing 2 % nanoscale sheet silicate			
	C2.1	C2.2	E2.3	C2.4
Thicknesses (μm)	40/10/150	20/10/20/10/140	5/10/35/10/140	20/10/20/10/140
Thickness of outer layer to thickness of all the PA layers (%)	100	50	12.5	50
PA of the inner layer	no inner layer	PA6	PA6	PA6 containing 2 % montmorillonite
Gloss (gloss units)	91	89	90	90
Cloudiness (%)	12	12	11	13
Number of holes after 250 strokes	13,5	11	7	15
Puncture work (N cm)	0,8	0,9	1.0	0.8
Coefficient of static friction, film/film at 23°C (-)	0.37	0.33	0.35	0.40
Shrinkage after production (%)	0.3	0.4	0.5	0,3
Producibility	no*	no*	Yes	no*

5 Table: Properties of films from Test Series 2.

Explanation relating to producibility:

* The film is so stiff that the film parison is not steady and forms folds when collapsed.

10

All the films have good optical properties, a high slip and a low shrinkage. Unduly large layer thicknesses of a polyamide 6 containing 2% nanodisperse montmorillonite results in a very stiff film that has disadvantages with regard to loop strength. In addition, such films prove to be unproducible as blown film. A film

having 5 μm -thick outer layer of polyamide 6 containing 2% nanodisperse montmorillonite avoids these disadvantages and meets the object set here.

Test Series 3

5

Five-layer blown films having the structure PA/HV//PA/HV//LDPE were coextruded and had an inner layer of pure polyamide 6 and a thin outer layer of polyamide 6 with montmorillonite dispersed in it. In this series, the concentration of the sheet silicate was varied. The thickness distribution is 5//10//35//10//140 μm .

10

Example 3.1 (E3.1):

Identical to Example 2.3, i.e. a film having the structure PA-2//HV//PA-1//HV//LDPE containing PA-2 and PA-1 from Comparison Examples 1.2 and 1.1.

15

Comparison Example 6 (C6):

Film as in Example 5 having the structure (5 % PA-2 + 95 % PA-1)//HV//PA-1//HV//LDPE.

20

Example 7 (E7):

Film as in Example 5 having the structure (10 % PA-2 + 90 % PA-1)//HV//PA-1//HV//LDPE.

25

Comparison Example 8 (C8):

Film as in Example 5 having the structure PA-4//HV//PA-1//HV//LDPE. PA-4 is a polyamide 6 containing 5 wt % of montmorillonite. The montmorillonite is present in dispersed form as platelets as a result of suitable digestion. The platelets have a thickness of approximately 1 nm and a diameter of 100 to 1000 nm.

30

The table below lists the properties measured on the five-layer films of Test S3:

Feature (unit)	Example (E) or Comparison Example (C) Structure PA/HV//PA'/HV//LDPE 5/10/35/10/140 μm PA' of the inner layer = pure PA6			
	E3.1	E3.2	E3.3	E3.4
Proportion of sheet silicate in the outer layer (wt %)	2	0.1	0.2	5
Gloss (gloss units)	90	63	85	93
Cloudiness (%)	11	20	13	12
Number of holes after 250 strokes	7	5.5	6.5	24
Puncture work (N cm)	1.0	1.0	1.0	0.6
Coefficient of static friction, film/film at 23°C (-)	0.35	0.30	0.32	0.32
Shrinkage after production (%)	0.5	0.6	0.6	0.5
Producibility	yes	yes	yes	no*

Table: Properties of films from Test Series 3.

5

Explanation relating to producibility:

* The film is so stiff that the film parison is unsteady and forms folds when collapsed.

10

Accordingly, an optimum concentration range of the nanodisperse nucleating agent in the outer layer is between 0.1 and 3 wt %. Unduly low loadings result in deteriorating optical properties, whereas unduly high loadings result in turn in an embrittling effect and in low loop strengths and problems during the manufacture.

Patent Claims

1. Multilayer film optionally comprising a heat-sealable coating having an outer polyamide layer containing nanoscale particulate nucleating agents and at least one further polyamide layer, characterized in that, for the polyamide forming the outer layer, use is made of at least 90% polyamide 6, relative to the total mass of the polyamide in said layer, and the smallest constituents of the particles dispersed in the outer layer forming a rigid unit in the dispersion having as a number-weighted average of all the constituents a dimension of not more than 100 nm in at least one direction that can be arbitrarily chosen for each constituent, in that, when the outer layer is cooled from the completely molten state at a cooling rate of between 10° and 20°C per minute, crystalline structures are produced that originate from the surface of the particles dispersed therein, in that all the further polyamide layers contain the particles contained in the outer layer at a level of not more than one tenth of the proportion by weight of the particles in the outer layer, and in that the thickness of the outer layer is less than 50% of the total thickness of all the layers containing polyamide.
2. Multilayer film according to Claim 1, characterized in that the proportion by weight of the particles dispersed in the outer layer, relative to the total weight of the composition forming the outer layer, is between 0.1 and 3%..
3. Multilayer film according to Claim 1 or 2, characterized in that, in addition to polyamide 6, the outer layer contains a polyamide selected from the group comprising polyamide 6, polyamide 10, polyamide 12, polyamide 66, polyamide 610, polyamide 6I, polyamide 612, polyamide 6/66, polyamide 6I/6T, polyamide MXD6, polyamide 6/6I, polyamide 6/6T, polyamide 6/IPDI, copolymers of monomers forming said polymers or mixtures of said polymers or copolymers.

4. Multilayer film according to one of Claims 1 to 3, characterized in that the particles dispersed in the outer layer comprise particles that have, in two mutually perpendicular directions that can be arbitrarily chosen for each particle, a dimension in each case of at least a tenth of the dimension of the particles in the direction with the smallest dimension.
5. Multilayer film according to one of Claims 1 to 4, characterized in that the particles dispersed in the outer layer are sheet silicates.
6. Multilayer film according to one of Claims 1 to 5, characterized in that it contains one or more EVOH-containing layers.
7. Multilayer film according to one of Claims 1 to 6, characterized in that it has an at least monolayer heat-sealable coating on that side of the multilayer film remote from the outer layer.
8. Multilayer film according to one of Claims 1 to 7, characterized in that it contains one or more coupling layers.
9. Multilayer film according to one of Claims 1 to 8, characterized in that, in addition to the outer layer and one or more further layers composed of polyamide and, optionally, conventional additives and also, optionally, one or more EVOH-containing layers, one or more heat-sealable coatings and also one or more coupling layers, it additionally contains one or more further polymeric layers or a layer of a metal oxide or nonmetal oxide between two inner layers.
10. Multilayer film according to one of Claims 1 to 9, characterized in that at least one outer layer, optionally also a plurality of or all the layers are subjected after extrusion to a stretching operation only in the longitudinal direction, only in the transverse direction, first in the longitudinal direction

- 25 -

and then in the transverse direction, simultaneously in the longitudinal direction and transverse direction or combinations thereof.

- 5 11. Multilayer film according to one of Claims 1 to 10, characterized in that it is produced as a blown film by coextrusion.
12. Use of a multilayer film according to one of Claims 1 to 13 for packaging foodstuffs.

"food" food

COMBINED DECLARATION AND POWER OF ATTORNEY

ATTORNEY DOCKET NO

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below next to my name. I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought

on the invention entitled

HIGH LUSTER, FLEXIBLE MULTILAYERED FILM WITH A POLYAMIDE OUTER LAYER CONTAINING NANODISPERSED FILLING MATERIAL AND UTILIZATION OF SAID FILM FOR PACKAGING FOODSTUFFS

the specification of which is attached hereto,

or was filed on **Oktober 4, 1999**

as a PCT Application Serial No. **PCT/EP99/07349**

I hereby state that I have reviewed and understand the contents of the above-identified specification, including the claims.

I acknowledge the duty to disclose information which is material to the patentability of this application in accordance with Title 37, Code of Federal Regulations, §1.56.

I hereby claim foreign priority benefits under Title 35, United States Code, §119 of any foreign application(s) for patent or inventor's certificate listed below and have also identified below any foreign application for patent or inventor's certificate having a filing date before that of the application on which priority is claimed:

Prior Foreign Application(s), the priority(ies) of which is/are to be claimed:

198 47 845.3	Germany	October 16, 1998
(Number)	(Country)	(Month/Day/Year Filed)

I hereby claim the benefit under Title 35, United States Code, §120 of any United States application(s) listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States application in the manner provided by the first paragraph of Title 35, United States Code, §112, I acknowledge the duty to disclose the material information as defined in Title 37, Code of Federal Regulations, §1.56 which occurred between the filing date of the prior application and the national or PCT international filing date of this application:

(Application Serial No.)	(Filing Date)	(Status)
		(patented, pending, abandoned)

(Application Serial No.)	(Filing Date)	(Status)
		(patented, pending, abandoned)

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

WW 5514-US

POWER OF ATTORNEY: As a named inventor, I hereby appoint the following attorney(s) and/or agent(s) to prosecute this application and to transact all business in the Patent and Trademark Office connected therewith:

JOSEPH C. GIL, Patent Office Registration Number 26,602

ARON PREIS, Patent Office Registration Number 29,426

LYNDANNE M. WHALEN, Patent Office Registration Number 29,457

THOMAS W. ROY, Patent Office Registration Number 29,582

RICHARD E. L. HENDERSON, Patent Office Registration Number 31,619

GODFRIED R. AKORLI, Patent Office Registration Number 28,779

N. DENISE BROWN, Patent Office Registration Number 36,097

NOLAND J. CHEUNG, Patent Office Registration Number 39,138

DIDERICO VAN EYL, Patent Office Registration Number 38,641

CAROLYN M. SLOANE, Patent Office Registration Number 44,339

JAMES R. FRANKS, Patent Office Registration Number 42,552

JACKIE ANN ZURCHER, Patent Office Registration Number 42,251

all of Bayer Corporation, Pittsburgh, Pennsylvania 15205-9741

Send Correspondence To:
Patent Department
Bayer Corporation
100 Bayer Road
Pittsburgh, Pennsylvania 15205-9741

Direct Telephone Calls To:

(412) 777-2349

FULL NAME OF SOLE OR FIRST INVENTOR Holger Eggers		INVENTOR'S SIGNATURE <i>Holger Eggers</i>	DATE 11.3.2001
RESIDENCE D 79117 Freiburg, Germany DEX		CITIZENSHIP German	
POST OFFICE ADDRESS Im Schuldorobel 22, D 79117 Freiburg, Germany			
FULL NAME OF SECOND INVENTOR Gregor Kaschel		INVENTOR'S SIGNATURE <i>Gregor Kaschel</i>	DATE 8.3.2001
RESIDENCE D 29699 Bomlitz, Germany DEX		CITIZENSHIP German	
POST OFFICE ADDRESS Uferstr. 37, D 29699 Bomlitz, Germany			
FULL NAME OF THIRD INVENTOR		INVENTOR'S SIGNATURE	DATE
RESIDENCE		CITIZENSHIP	
POST OFFICE ADDRESS			
FULL NAME OF FOURTH INVENTOR		INVENTOR'S SIGNATURE	DATE
RESIDENCE		CITIZENSHIP	
POST OFFICE ADDRESS			
FULL NAME OF FIFTH INVENTOR		INVENTOR'S SIGNATURE	DATE
RESIDENCE		CITIZENSHIP	
POST OFFICE ADDRESS			
FULL NAME OF SIXTH INVENTOR		INVENTOR'S SIGNATURE	DATE
RESIDENCE		CITIZENSHIP	
POST OFFICE ADDRESS			
FULL NAME OF SEVENTH INVENTOR		INVENTOR'S SIGNATURE	DATE
RESIDENCE		CITIZENSHIP	
POST OFFICE ADDRESS			

WW 5514 US